




GTN 9 Z7

APPLICATION

- Suitable for machining steel and stainless steel
- straight front angle for grooving or parting off



GRADE Z7

This PVD coated fine grained WC-Co carbide within ISO-grade ranges P25 -P40 and K20 -K40 for machining of steel and stainless steel.

	STEEL	STAINLESS	CAST IRON	NON FERROUS	S.ALLOYS	HEAT TREATED
GROUP	P30	M30	K30			
Sfm ft/min	295 - 492	164 - 295	279 - 459			
Fn Inch/Z	0.0031 - 0.0138	0.0035 - 0.0124	0.0031 - 0.0138			
ap Inch						

LEGEND

Sfm (Vc)	Surface Feet per Minute
Fn (ipr)	Feed per revolution
Fz (ipt)	Feed per tooth
ap	Depth of cut

FORMULA

$S \text{ (RPM)} = Sfm * 12 / \pi / D = \text{rev per minute}$
$F \text{ (IPR, inch per revolution)} = S * Fn = \text{feed per minute}$
$F \text{ (IPM, inch per minute)} = S * Fz * n.\text{flutes} = \text{feed per minute}$
$Sfm = S * D * \pi / 12$