


# CCMT.UR 21.50 Z5P



## APPLICATION

- Suitable for fine to heavy machining of steels
- Continuous and interrupted cut



## GRADE Z5P

It is a PVD coated fine grained WC-Co carbide within ISO range P25-P40, for fine to heavy machining of steels

	STEEL	STAINLESS	CAST IRON	NON FERROUS	S.ALLOYS	HEAT TREATED
GROUP	P25 - P40	M25 - M40	K25 - K40			
Sfm ft/min	541 - 755	295 - 410	443 - 607			
Fn Inch/rev	.003 - .005	.004 - .005	.003 - .005			
ap Inch	.008 - .079	.008 - .079	.008 - .079			

### LEGEND

Sfm (Vc)	Surface Feet per Minute
Fn (ipr)	Feed per revolution
Fz (ipt)	Feed per tooth
ap	Depth of cut

### FORMULA

$S \text{ (RPM)} = \text{Sfm} * 12 / \pi / D = \text{rev per minute}$
$F \text{ (IPR, inch per revolution)} = S * \text{Fn} = \text{feed per minute}$
$F \text{ (IPM, inch per minute)} = S * Fz * n.\text{flutes} = \text{feed per minute}$
$\text{Sfm} = S * D * \pi / 12$

**TURNING CARBIDE INSERT**