

General Purpose Carbide End Mills



SERIES: General Purpose Carbide End Mills Z4TW

MATERIAL		CONDITIONS		CUTTING DIAMETER								
				1/8"	1/4"	5/16"	3/8"	1/2"	5/8"	3/4"	1"	
		Under 32 HRc	Over 32 HRc	CHIP PER TOOTH								
STAINLESS STEELS		ISO-M										
Precipitation 13-8, 15-5, 17-4PH	Slotting .5 x Dia.	110-200	80-115	0.0005	0.0010	0.0012	0.0014	0.0020	0.0025	0.0030	0.0040	
	Profiling ≤ .5 x Dia.	110-200	80-115	0.0006	0.0012	0.0015	0.0018	0.0025	0.0031	0.0038	0.0050	
Austenitic 302, 303, 304L, 316L	Slotting .5 x Dia.	150-275	80-180	0.0005	0.0011	0.0014	0.0016	0.0023	0.0029	0.0035	0.0046	
	Profiling ≤ .5 x Dia.	150-275	80-180	0.0007	0.0014	0.0018	0.0021	0.0030	0.0038	0.0045	0.0060	
Martensitic 403, 410, 416	Slotting .5 x Dia.	200-400	80-160	0.0005	0.0011	0.0014	0.0016	0.0023	0.0029	0.0035	0.0046	
	Profiling ≤ .5 x Dia.	200-400	80-160	0.0007	0.0014	0.0018	0.0021	0.0030	0.0038	0.0045	0.0060	
HIGH TEMP ALLOYS		ISO-S										
Cobalt Base Stellite, Haynes 25, 188, X-40, L-605	Slotting .5 x Dia.	60-125	60-125	0.0004	0.0007	0.0009	0.0011	0.0015	0.0019	0.0023	0.0030	
	Profiling ≤ .5 x Dia.	60-125	60-125	0.0005	0.0010	0.0012	0.0014	0.0020	0.0025	0.0030	0.0040	
Nickel Base Inconel 600, 625, 718, Nickel 200, 270, Invar, Monel 400, 405, K-Monel, PermaNickel 300, Incoly 600	Slotting .5 x Dia.	60-125	60-125	0.0004	0.0007	0.0009	0.0011	0.0015	0.0019	0.0023	0.0030	
	Profiling ≤ .5 x Dia.	60-125	60-125	0.0005	0.0010	0.0012	0.0014	0.0020	0.0025	0.0030	0.0040	
Iron Base Incoloy 800-802, Multimet N-155, Timken 16-26-6	Slotting .5 x Dia.	60-125	60-125	0.0004	0.0007	0.0009	0.0011	0.0015	0.0019	0.0023	0.0030	
	Profiling ≤ .5 x Dia.	60-125	60-125	0.0005	0.0010	0.0012	0.0014	0.0020	0.0025	0.0030	0.0040	
STEELS		ISO-P										
High Strength Steels 4140, 4340, 52100	Slotting .5 x Dia.	150-300	80-180	0.0005	0.0010	0.0012	0.0014	0.0020	0.0025	0.0030	0.004	
	Profiling ≤ .5 x Dia.	150-300	80-180	0.0006	0.0010	0.0012	0.0018	0.0025	0.0031	0.0038	0.005	
High Alloy Steels - Mold & Die A-2, P20, 01, 02, D2, H-13	Slotting .5 x Dia.	150-275	80-185	0.0005	0.0010	0.0012	0.0014	0.0020	0.0025	0.0030	0.004	
	Profiling ≤ .5 x Dia.	150-275	80-185	0.0006	0.0010	0.0012	0.0018	0.0025	0.0031	0.0038	0.005	
Medium Alloy Steels 200, 250, 300	Slotting .5 x Dia.	175-350	100-225	0.0005	0.0010	0.0012	0.0014	0.0020	0.0025	0.0030	0.004	
	Profiling ≤ .5 x Dia.	175-350	100-225	0.0006	0.0010	0.0012	0.0018	0.0025	0.0031	0.0038	0.005	
Low Alloy Steels-Maraging 10XX, 11XX, 13XX	Slotting .5 x Dia.	200-450	100-250	0.0006	0.0012	0.0015	0.0018	0.0025	0.0031	0.0038	0.005	
	Profiling ≤ .5 x Dia.	200-450	100-250	0.0007	0.0014	0.0018	0.0021	0.0030	0.0038	0.0045	0.006	
CAST IRONS		ISO-K										
Ductile Iron Ductile Cast Iron	Slotting .5 x Dia.	120-325	80-140	0.0005	0.0010	0.0012	0.0014	0.0020	0.0025	0.0030	0.0040	
	Profiling ≤ .5 x Dia.	120-325	80-140	0.0006	0.0012	0.0015	0.0018	0.0025	0.0031	0.0038	0.0050	
Cast Iron Grey Cast Iron	Slotting .5 x Dia.	250-425	125-285	0.0005	0.0010	0.0012	0.0014	0.0020	0.0025	0.0030	0.0040	
	Profiling ≤ .5 x Dia.	250-425	125-285	0.0006	0.0012	0.0015	0.0018	0.0025	0.0031	0.0038	0.0050	
TITANIUMS		ISO-S										
Titanium Alloys 6AL-4V, ASTM 1, 2, 3, 6AL-2S For 5553, decrease SFM and IPM by 25%	Slotting .5 x Dia.	140-200	90-145	0.0005	0.0010	0.0012	0.0014	0.0020	0.0025	0.0030	0.0040	
	Profiling ≤ .5 x Dia.	140-200	90-145	0.0006	0.0012	0.0015	0.0018	0.0025	0.0031	0.0038	0.0050	
ALUMINUM		ISO-N										
Aluminum Alloys 6061-T6, 7075	Slotting .5 x Dia.	600-1000	NA	0.0006	0.0012	0.0015	0.0018	0.003	0.005	0.006	0.0080	
	Profiling ≤ .5 x Dia.	600-1000	NA	0.0007	0.0014	0.0018	0.0025	0.0035	0.006	0.0068	0.0100	